



1720 Prosperity Court
Chippewa Falls, WI 54729
www.chemceed.com

Ph: (715)726-2300
Fax: (715)726-2314
contact@chemceed.com

SEBACIC ACID-GRANULAR

SALES SPECIFICATIONS

CAS Number: 111-20-6

PROPERTY	LIMITS
Assay, %	99.5 Minimum
Appearance	White Granular
Granularity	85 min %, 60 Mesh
Moisture, %	0.30 Maximum
Ash, %	0.03 Maximum
Color, APHA	25 Maximum
Melting Point	131-134.5 °C

123015-00-99/101/106/150/622