



1720 Prosperity Court
Chippewa Falls, WI 54729
www.chemceed.com

Ph: (715)726-2300
Fax: (715)726-2314
inquiry@chemceed.com

C8-C10 ALKYL GLYCIDYL ETHER

SALES SPECIFICATIONS

CAS Number: 68609-96-1

| PROPERTY | LIMITS |
|-------------------------------|---------------|
| Color, APHA | ≤20 Maximum |
| Viscosity, mPa.s (25°C) | 3-8 |
| Epoxy Equivalent Weight, e/eq | 222-250 |
| Hydrolyzable Chloride, % | ≤0.20 Maximum |
| Inorganic Chlorine, mg/kg | ≤20 Maximum |
| Moisture Content, % | ≤0.10 Maximum |
| Free ECH, ppm | ≤10 Maximum |

05232023-AH-622